

# Thick-film zinc repair compound LZ-09

Zinc repair compound, light silver, 1-component.



## Product description

### Application range

For repairing flaws on hot-dip galvanised steel parts, moreover for galvanised surfaces damaged by grinding or welding, and for non-galvanised small steel parts, that are to be matched to galvanized constructions.

### Note

**According to the requirements of standard DIN EN ISO 1461 edition 2022-12.**

### Properties

- excellent corrosion protection
- different colour shades
- easy application
- best praxis
- high Zinc content

### Delivery sizes

100 ml  
250 ml  
500 ml  
1.0 l  
2.5 l  
5.0 l  
12 kg

### Colour shades

Available in 6 different shades from light to dark, see ReiColor colour chart no. 050.

### Product types

LZ-09.00.0000.0 light  
LZ-09.00.0001.1 light  
LZ-09.00.0002.1 middle  
LZ-09.00.0004.1 middle  
LZ-09.00.0008.1 dark  
LZ-09.00.0016.1 dark

### Gloss level

matt

### Application rate

approx. 8 m<sup>2</sup>/l

### Density

approx. 1.2 kg/l

### Storage stability / shelf-life

Min. 3 years at room temperature and dry storage.

## Handling

<b>Working instruction</b>	Stir thoroughly before use.
<b>Substrate preparation</b>	Bottom chord clean thoroughly before applying. Thoroughly remove loose parts such as rust, white rust, scale, carbon black, grease and other contaminations.
<b>Application method</b>	Undiluted mainly by brushing and rolling.
<b>Application temperature</b>	The temperature of the zinc bottom chord should be between +5°C and approx. + 50°C. Especially at deep temperatures it is to be paid attention to the cool zinc surfaces neither being covered with condensate nor with frozen dew. Otherwise there might arise spallings after overpainting the surface. In case of very high temperatures the dissolvents flash off too quickly due to the hot surface. As a consequence further processing of <b>LZ-09</b> is not possible any more.
<b>Solvents</b>	ReiColor <b>VE-50</b> , ReiColor <b>VK-30</b> or ReiColor <b>VK-80</b>
<b>Dry film thickness</b>	100 µm per application
<b>Drying method</b>	air drying Dust dry after approx. 1 hour. Recommended drying time: over night.
<b>Over-paintable</b>	after complete drying, e.g. with ReiColor <b>LZ-80</b> , ReiColor <b>ZY-20</b> , ReiColor <b>ZL-22</b>

## Notes

<b>Safety instructions VOC</b>	Cat. A/i, 500 g/l (2010). This product contains 500 g/l VOC max.
<b>Hazard notes</b>	Please observe technical data sheet and safety data sheet before use.

**Data base:** All technical information in this data sheet is based on laboratory tests and may deviate from values actually resulting from practical use.

**Disclaimer:** The above data are based on our present knowledge and experience provided that the material is stored properly and applied appropriately. The data are exclusively intended to describe the products and do not constitute warranted properties in any legal sense. We reserve the right to make changes to product specifications at any time. Our technical advice - whether verbal, in writing or by way of trials - is given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release the customer from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

**The current version of the technical data sheet with the newest release date is available on our homepage [www.reicolor.de/Produkte](http://www.reicolor.de/Produkte). With the publication of a new edition of this technical data sheet all information in previous data sheets is no longer valid.**

Reicolor Chemie-GmbH  
Werkstraße 19 + 21  
D-90518 Altdorf b. Nürnberg  
Tel.: +49(0)9187/97 03-0  
<https://www.reicolor.de>



Release date: 15.07.2024